

IN THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A gypsum board, comprising:
 - a. a gypsum layer having a first face and a second face and comprising set gypsum; and
 - b. first and second facers affixed to said first and second faces, said first facer being a fibrous mat comprising a non-woven, glass fiber web bonded together with a resinous binder, and said glass fibers consisting essentially of chopped glass fibers having an average fiber diameter ranging from about 9.5 to 12.5 μm .
2. (previously presented) A gypsum board as recited by claim 1, wherein said chopped glass fibers are composed of at least one member selected from the group consisting of E glass, C glass, T glass, sodium borosilicate glass, and mixtures thereof.
3. (previously presented) A gypsum board as recited by claim 1, wherein said chopped glass fibers are composed of E glass.
4. (previously presented) A gypsum board as recited by claim 1, wherein at least about 90% by weight of said chopped glass fibers have a diameter ranging between about 9.5 and 12.5 μm .

5. (previously presented) A gypsum board as recited by claim 1, wherein at least about 95% by weight of said chopped glass fibers have a diameter ranging between about 9.5 and 12.5 μm .
6. (previously presented) A gypsum board as recited by claim 1, wherein at least about 97% by weight of said chopped glass fibers have a diameter ranging between about 9.5 and 12.5 μm .
7. (previously presented) A gypsum board as recited by claim 1, wherein said chopped glass fibers have an average fiber length ranging from about 6 to 12 mm.
8. (previously presented) A gypsum board as recited by claim 1, wherein at least a majority of said chopped glass fibers have a fiber length ranging from about 6 to 18 mm.
9. (original) A gypsum board as recited by claim 1, wherein said resinous binder is composed of at least one member selected from the group consisting of urea formaldehyde; conventional modified urea formaldehyde; acrylic resin; melamine resin; high nitrogen melamine resin; homopolymer and copolymer of polyacrylic acid having a molecular weight of less than 10,000; crosslinking acrylic copolymer; crosslinked vinyl chloride acrylate copolymer; and modified acrylic latex binder.
10. (original) A gypsum board as recited by claim 1, wherein said resinous binder is composed of a modified acrylic latex binder.

11. (original) A gypsum board as recited by claim 9, wherein said resinous binder further comprises a cross-linker in an amount ranging up to about 10 weight percent.
12. (original) A gypsum board as recited by claim 11, wherein said cross linker is present in an amount ranging from about 2 to 5 weight percent.
13. (original) A gypsum board as recited by claim 11, wherein said resinous binder comprises melamine formaldehyde.
14. (original) A gypsum board as recited by claim 1, wherein said resinous binder has a glass transition temperature ranging from about 15 to 45°C.
15. (original) A gypsum board as recited by claim 1, wherein said resinous binder further comprises at least one water repellant agent.
16. (cancelled)
17. (original) A gypsum board as recited by claim 1, wherein said fibrous mat has a basis weight ranging from about 0.6 to 2.2 pounds per 100 square feet.
18. (original) A gypsum board as recited by claim 17, wherein said fibrous mat has a basis weight ranging from about 0.9 to 2.2 pounds per 100 square feet.
19. (original) A gypsum board as recited by claim 18, wherein said fibrous mat has a basis weight of about 1.25 ± 0.2 pounds per 100 square feet.
20. (original) A gypsum board as recited by claim 1, said second facer comprising kraft paper.

21. (original) A gypsum board as recited by claim 1, said second facer comprising a fibrous mat.
22. (currently amended) A gypsum board as recited by claim 1, said second facer being a fibrous mat comprising a non-woven, glass fiber web bonded together with a resinous binder, and said glass fibers consisting essentially of chopped glass fibers having an average fiber diameter ranging from about 9.5 to 12.5 μm .
23. (original) A gypsum board as recited by claim 1, wherein said gypsum core further comprises at least one water repellant agent.
24. (original) A gypsum board as recited by claim 1, wherein said gypsum core further comprises reinforcing fiber.
25. (original) A gypsum board as recited by claim 1, wherein said gypsum core further comprises a biocide.
26. (original) A gypsum board as recited by claim 1, said board having flame resistance sufficient to pass the test of ASTM Method E84, Class 1.
27. (currently amended) In a gypsum board having a first face and a second face and a non-woven fibrous mat affixed to at least one of said faces, the improvement wherein said mat comprises a glass fiber web bonded together with a resinous binder, said glass fibers consisting essentially of chopped glass fibers having an average fiber diameter ranging from about 9.5 to 12.5 μm .
28. (withdrawn) A process for manufacturing an article comprising a hydraulic set material layer having first and second faces, and first and second facers affixed

thereto, at least said first facer comprising a non-woven, fibrous mat, the process comprising:

- a. providing said non-woven, fibrous mat having a fibrous web composed of chopped continuous glass fibers having an average fiber diameter ranging from about 9.5 to 12.5 μm bound together with a resinous binder;
 - b. forming an aqueous slurry comprising at least one member selected from the group consisting of anhydrous calcium sulfate, calcium sulfate hemi-hydrate, and hydraulic setting cement;
 - c. distributing the slurry to form a layer on said first facer;
 - d. applying said second facer onto the top of said layer;
 - e. separating the resultant laminate into individual articles; and
 - f. drying the articles.
29. (currently amended) A fibrous mat comprising a non-woven glass fiber web bonded together with a resinous binder, said glass fibers consisting essentially of chopped glass fibers having an average fiber diameter ranging from about 9.5 to 12.5 μm .
30. (previously presented) A fibrous mat as recited by claim 29, wherein at least about 90% by weight of said chopped glass fibers have a diameter ranging between about 9.5 and 12.5 μm .
31. (original) A fibrous mat as recited by claim 29, said mat having a permeability of at least about 300 cfm/ft^2 measured by the Frazier test.
32. (currently amended) A hydraulic set board, comprising:

- a. a hydraulic set material layer having a first and a second face; and
- b. first and second facers affixed to said first and second faces, at least of said first facer being a fibrous mat comprising a non-woven, glass fiber web bonded together with a resinous binder, said glass fibers consisting essentially of chopped glass fibers having an average fiber diameter ranging from about 9.5 to 12.5 μm .